






A5




Elastomeric composition for preparing olefinic elastomer crosslinked foam and use thereof

Patent number: EP1229076
Publication date: 2002-08-07
Inventor: SUEDA TAKANORI (JP); YASAKA NAOTO (JP); YOO CHONG-SUN (KR); YOON JEONG-SIK (KR); CHOI KYUNG-MAN (KR)
Applicant: MITSUI CHEMICALS INC (JP)
Classification:
- international: C08L23/16; C08J9/00; C08K5/098
- european: C08K5/098; C08L23/08A1
Application number: EP20020001948 20020201
Priority number(s): JP20010025918 20010201

Also published as:

 US6720364 (B2)
 US2002143077 (A)
 EP1229076 (B1)
 DE60200956T (T2)
 DE60200956D (T2)

Cited documents:

 EP0997493
 WO9748538
 EP0605843

Report a data error he**Abstract of EP1229076**

The elastomeric composition for preparing an olefinic elastomer crosslinked foam according to the present invention contains an ethylene/ alpha -olefin copolymer (A) having a specific density and MFR, an organic peroxide (D), a crosslinking assistant (E), a foaming agent (F), an organic metal compound (G), and, as necessary, a high pressure low density polyethylene (B) having a specific MFR, and an ethylene/vinyl acetate copolymer (C) having a specific amount of vinyl acetate and a specific MFR. An olefinic elastomer crosslinked foam of the present invention can be obtained by crosslinking and foaming the above composition. Further, another olefinic elastomer crosslinked foam of the present invention can be obtained by a secondary compression of the above crosslinked foam. The footwear part of the present invention is made of these crosslinked foams. The present invention provides an elastomeric composition for preparing an olefinic elastomer crosslinked foam that can provide an olefinic elastomer crosslinked foam having an Asker C hardness of 20 to 80, a low specific gravity, a low compression set, and excellent tear strength and impact resilience; and a crosslinked foam made of this. Furthermore, the present invention provides footwear parts made of the above crosslinked foam.

Data supplied from the esp@cenet database - Worldwide

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 229 076 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
18.08.2004 Bulletin 2004/34

(51) Int Cl.7: **C08L 23/16, C08J 9/00,
C08K 5/098**

(21) Application number: **02001948.5**

(22) Date of filing: **01.02.2002**

(54) **Elastomeric composition for preparing olefinic elastomer crosslinked foam and use thereof**
Elastomierzusammensetzung für vernetzte Olefinschäume und ihre Verwendung
Compositions élastomérées pour la preparation de mousses oléfiniques et leur utilisation

(84) Designated Contracting States:
DE FR IT

(30) Priority: **01.02.2001 JP 2001025918**

(43) Date of publication of application:
07.08.2002 Bulletin 2002/32

(73) Proprietor: **MITSUI CHEMICALS, INC.**
Tokyo (JP)

(72) Inventors:
• **Sueda, Takanori**
Ichihara-shi, Chiba (JP)
• **Yasaka, Naoto**
Ichihara-shi, Chiba (JP)

• **Yoo, Chong-Sun**
Pusan (KR)
• **Yoon, Jeong-Sik**
Pusanjin-ku, Pusan (KR)
• **Choi, Kyung-Man**
Pusanjin-ku, Pusan (KR)

(74) Representative: **HOFFMANN - EITLE**
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(56) References cited:
EP-A- 0 605 843 **EP-A- 0 997 493**
WO-A-97/48538

EP 1 229 076 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

BACKGROUND OF THE INVENTION

5 Field of the Invention

[0001] The present invention relates to an elastomeric composition for preparing an olefinic elastomer crosslinked foam and use thereof, and more specifically, an elastomeric composition for preparing an olefinic elastomer crosslinked foam that can provide an olefinic elastomer crosslinked foam having an Asker C hardness of 20 to 80, a low specific gravity, a low compression set (CS), and an excellent tear strength and impact resilience, and to an olefinic elastomer crosslinked foam made of this.

Description of the Related Art

15 [0002] Techniques using crosslinked foams to obtain a resin having a low specific gravity, i.e. a light weight, a high flexibility and a high mechanical strength are broadly applied to interior and exterior building materials, automotive parts such as interior materials or door glass runs, wrapping materials, articles of daily use, etc. Such techniques are used because mere foaming a resin for weight reduction leads to a reduction of mechanical strength, but, in contrast, binding molecular chains by crosslinking reaction of a resin enables weight reduction by foaming while avoiding reduction of mechanical strength.

20 [0003] In addition, resin crosslinked foams are also used for soles (mainly, midsoles) of athletic shoes etc. This is because materials are needed that are light and have a high mechanical strength enough to avoid deformation due to long-term use and withstand harsh use conditions.

25 [0004] Conventionally, crosslinked foams of an ethylene/vinyl acetate copolymer are used for soles and is publicly known. However, such crosslinked foams, which are molded using an ethylene/vinyl acetate copolymer composition, have a high specific gravity and are insufficient in terms of a low compression set, and therefore when used for a sole for example, a problem arises that the sole is heavy and is compressed by long-term use, so that mechanical strength such as impact resilience is lost.

30 [0005] EP-A-0 997 493 discloses a crosslinked olefin elastomer foam and elastomer compositions therefore. There is no disclosure of the presence of a metal compound with unsaturated carbon bonds in the elastomer compositions.

[0006] EP-A-0 605 843 is directed to a process for the vulcanization of ethylene-vinyl acetate polymers using zinc oxide, an organic peroxide and zinc diacrylate. This document does not disclose the presence of ethylene polymers and foaming agents.

35 [0007] National Publication of International Patent Application No. 9-501447 and Japanese Patent Laid-Open No. 11-206406 describe a crosslinked foam using an ethylene/ α -olefin copolymer, and a crosslinked foam using a mixture of an ethylene/vinyl acetate copolymer and an ethylene/ α -olefin copolymer, respectively. Some improvements in terms of a low specific gravity and a low compression set are attained, but adequate performance has not been obtained in these inventions.

40 [0008] Therefore, there is a need for an elastomeric composition for preparing an olefinic elastomer crosslinked foam that can provide an olefinic elastomer crosslinked foam having an Asker Chardness of 20 to 80, a low specific gravity, a low compression set (CS) and an excellent tear strength and impact resilience, and a crosslinked foam made of this.

45 [0009] The present invention intends to solve the above problems accompanying the prior art, and an object of the present invention is to provide an elastomeric composition for preparing an olefinic elastomer crosslinked foam that can provide an olefinic elastomer crosslinked foam having an Asker C hardness of 20 to 80, a low specific gravity and a low compression set (CS) and furthermore having excellent tear strength and impact resilience, and a crosslinked foam made of this.

[0010] Another object of the present invention is to provide a footwear part made of the above olefinic elastomer crosslinked foam, such as a sandals and a sole, midsole, and innersole of shoes.

50 SUMMARY OF THE INVENTION

[0011] The elastomeric composition for preparing an olefinic elastomer crosslinked foam of the present invention comprises

55 an ethylene/ α -olefin copolymer (A) which contains 85 to 99 mole% of units derived from ethylene and which has a density (ASTM D 1505) of 880 to 920 kg/m³ and a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) MFR_{2.16} of 0.1 to 10 g/10 min; optionally, a high pressure low density polyethylene (B) which contains less than 1 mole% of units derived from

an α -olefin having 3 to 10 carbon atoms and which has a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) of 0.1 to 50 g/10 min;
 optionally, an ethylene/vinyl acetate copolymer (C) which has a vinyl acetate content of 10 to 30% by weight and a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) of 0.1 to 50 g/10 min;
 5 an organic peroxide (D);
 a crosslinking assistant (E);
 a foaming agent (F); and
 0.05 to 5 parts by weight, based on 100 parts by weight of the total amount of the ethylene/ α -olefin copolymer (A), the high pressure low density polyethylene (B) and the ethylene/vinyl acetate copolymer (C), of an organic metal
 10 compound (G) which is a compound of metal selected from Groups 2 to 12 of the periodic table and which has at least two groups containing unsaturated carbon bond and at least one atom selected from oxygen, sulfur and nitrogen per molecule.

[0012] This elastomeric composition may further comprise, based on 100 parts by weight of the ethylene/ α -olefin copolymer (A), 5 to 100 parts by weight of a high pressure low density polyethylene (B), and/or 5 to 1,900 parts by weight of an ethylene/vinyl acetate copolymer (C).

[0013] The α -olefin in the above ethylene/ α -olefin copolymer (A) is usually an α -olefin having 3 to 10 carbon atoms.

[0014] There may be used, as the above ethylene/ α -olefin copolymer (A), a mixture of two or more ethylene/ α -olefin copolymers having a molecular weight distribution (Mw/Mn) determined by gel permeation chromatography (GPC) of 1.5 to 4, and a ratio (MFR₁₀/MFR_{2.16}) of a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load), MFR_{2.16} to a melt flow rate (ASTM D 1238, 190°C, 10 kg load), MFR₁₀, of 5 to 20.

[0015] The above mixture of two or more of the ethylene/ α -olefin copolymers is preferably produced by blending or multistage polymerization so that the molecular weight distribution (Mw/Mn) determined by GPC can be within a range of 2.3 to 6.

[0016] The above organic metal compound (G) generally has at least two $\text{CH}_2=\text{CH}-\text{CO}-\text{O}-$ or $\text{CH}_2=\text{C}(\text{CH}_3)-\text{CO}-\text{O}-$ groups per molecule.

[0017] The above organic metal compound (G) is preferably an organic zinc compound.

[0018] The organic zinc compound is preferably zinc diacrylate or zinc dimethacrylate.

[0019] The above organic metal compound (G) is contained in the above elastomeric composition in a proportion of 0.05 to 5 parts by weight based on 100 parts by weight of the total amount of the ethylene/ α -olefin copolymer (A), the high pressure low density polyethylene (B) and the ethylene/vinyl acetate copolymer (C). However, since components (B) and (C) are optional components, the amount of these components may be 0 part by weight.

[0020] The olefinic elastomer crosslinked foam of the present invention is obtained by crosslinking and foaming the above elastomeric composition for preparing an olefinic elastomer crosslinked foam of the present invention.

[0021] The olefinic elastomer crosslinked foam of the present invention may be a crosslinked foam obtained by a secondary compression of the crosslinked foam of the present invention.

[0022] The secondary compression is usually performed under conditions of a temperature of 130°C to 200°C, a load of 30 to 300 kg/cm² for 5 to 60 minutes.

[0023] These crosslinked foams desirably have a specific gravity (JIS K 7222 (g/cm³)) of 0.05 to 0.25, a surface hardness (Asker C hardness) of 20 to 80, and a gel fraction of 70% or more.

[0024] The footwear part of the present invention is made of the above olefinic elastomer crosslinked foam of the present invention.

[0025] Examples of the footwear parts include midsoles, innersoles, soles, etc.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0026] Now, the elastomeric composition for preparing an olefinic elastomer crosslinked foam of the present invention and a use thereof are described in detail.

[0027] The elastomeric composition for preparing an olefinic elastomer crosslinked foam of the present invention is an uncrosslinked unfoamed composition which is to be crosslinked and foamed by heating, and it comprises an ethylene/ α -olefin copolymer (A), an organic peroxide (D), a crosslinking assistant (E), a foaming agent (F), an organic metal compound (G), and as necessary, a high pressure low density polyethylene (B) and an ethylene/vinyl acetate copolymer (C).

Ethylene/ α -olefin copolymer (A)

[0028] Ethylene/ α -olefin copolymer (A) used in the present invention is a low crystalline random copolymer composed of ethylene and an α -olefin containing 3 to 10 carbon atoms, and has a density (ASTM D 1505) of 880 to 920 kg/m³

and a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load), $MFR_{2.16}$, of 0.1 to 10 g/10 min, preferably 0.5 to 10 g/10 min, and more preferably 0.5 to 5 g/10 min.

[0029] Moreover, the molecular weight distribution (Mw/Mn) of ethylene/ α -olefin copolymer (A) determined by gel permeation chromatography (GPC) is preferably within a range of 1.5 to 4. By using an ethylene/ α -olefin copolymer (A) having a molecular weight distribution (Mw/Mn) within the above range, a composition which is capable for giving an elastomer crosslinked foam excellent in terms of high mechanical strength and low compression set can be obtained.

[0030] The above molecular weight distribution (Mw/Mn) was determined using GPC-150C (Millipore) as follows.

[0031] As a separation column, TSK GNH HT having a diameter of 72 mm and a length of 600 mm was used, the column temperature was set at 140°C, and o-dichlorobenzene (Wako Pure Chemical Industries, Ltd.) and 0.025% by weight BHT (Takeda Chemical Industries, Ltd.) as an antioxidant were used as a mobile phase. 500 μ l of the sample having a concentration of 0.1% by weight, was poured into the column and transferred by the mobile phase fed at a rate of 1.0 ml/min. A differential refractometer was used as a detector. Using an EPR having a known Mw and Mn as a standard sample, the molecular weight was determined.

[0032] The α -olefin to be copolymerized with ethylene is preferably an α -olefin having 3 to 10 carbon atoms, and examples of such α -olefins include propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 4-methyl-1-pentene, etc., and of these, propylene, 1-butene, 1-hexene, 4-methyl-1-pentene and 1-octene are particularly preferable. These α -olefins are used singly or in combination of two or more.

[0033] The ethylene/ α -olefin copolymer (A) contains a unit derived from ethylene at an amount of 85 to 99 mole %, preferably 85 to 98 mole %, and a unit derived from an α -olefin (preferably, those having 3 to 10 carbon atoms) at an amount of usually 1 to 15 mole %, preferably 2 to 15 mole %.

[0034] The composition of the ethylene/ α -olefin copolymer (A) is generally determined by measuring ^{13}C -NMR spectrum of the sample obtained by homogenously dissolving about 200 mg of the ethylene/ α -olefin copolymer in 1 ml of hexachlorobutadiene in a 10 mm ϕ sample tube under conditions of a temperature of 120°C, a frequency of 25.05 MHz, a spectrum width of 1,500 Hz, a pulse-repetition time of 4.2 sec, and a pulse width of 6 μ sec.

[0035] In addition to the above units, the ethylene/ α -olefin copolymer (A) may contain units derived from other polymerizable monomers to the extent that they do not impair the objects of the present invention.

[0036] Examples of preferable ethylene/ α -olefin copolymers (A) include an ethylene/propylene random copolymer, an ethylene/1-butene random copolymer, an ethylene/propylene/1-butene random copolymer, an ethylene/1-hexene random copolymer, an ethylene/4-methyl-1-pentene random copolymer, an ethylene/1-octene random copolymer, etc. These copolymers may be used in combination of two or more.

[0037] As for the flow properties of the ethylene/ α -olefin copolymer (A) used in the present invention, the ratio ($MFR_{10}/MFR_{2.16}$) of a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load), $MFR_{2.16}$, to a melt flow rate (ASTM D 1238, 190°C, 10 kg load), MFR_{10} , is preferably within a range of 5 to 20.

[0038] Furthermore, as the ethylene/ α -olefin copolymer (A), two or more ethylene/ α -olefin copolymers having different composition and molecular weight can also be used in combination. For example, the following composition is preferably used, that is, one comprising: 5 to 95 parts by weight of an ethylene/ α -olefin copolymer (A-1) having a density (ASTM D 1505) of 880 kg/m³ to less than 900 kg/m³, a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) of 0.1 to 50 g/10 min, and a molecular weight distribution (Mw/Mn) determined by GPC of 1.5 to 4; and 5 to 95 parts by weight of an ethylene/ α -olefin copolymer (A-2) having a density (ASTM D 1505) of 900 to 920 kg/m³, a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) of 0.1 to 50 g/10 min, and a molecular weight distribution (Mw/Mn) determined by GPC of 1.5 to 4 (the total amount of both copolymers is 100 parts by weight). Two or more types of these copolymers (A-1) and (A-2) can also be used.

[0039] The molecular weight distribution (Mw/Mn) of the above mixture of two or more of the ethylene/ α -olefin copolymers determined by GPC is preferably within a range of 2.3 to 6.

[0040] The above ethylene/ α -olefin copolymer (A) can be produced by a previously known method involving the use of a vanadium, titanium or metallocene catalyst.

[0041] To obtain a composition composed of component (A-1) and component (A-2), either a method of blending these components or a method of polymerizing different compositions by multistage polymerization may be selected.

High pressure low density polyethylene (B)

[0042] High pressure low density polyethylene (B) that is optionally used in the present invention, is a polyethylene resin produced by radical polymerization of ethylene or both ethylene and an α -olefin having 3 to 10 carbon atoms, using a publicly known tubular reactor or an autoclave reactor, in the presence of a radical polymerization catalyst under high pressure.

[0043] The α -olefin to be copolymerized with ethylene is an α -olefin having 3 to 10 carbon atoms, and examples of such α -olefins include propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 4-methyl-1-pentene, etc., and of these, propylene, 1-butene, 1-hexene, 4-methyl-1-pentene and 1-octene are preferable. These

α -olefins are used singly or in combination of two or more.

[0044] The high pressure low density polyethylene (B) contains units derived from an α -olefin having 3 to 10 carbon atoms at an amount of less than 1 mole %.

[0045] The composition of the high pressure low density polyethylene (B) is determined by the same measurement method as for the composition of the ethylene/ α -olefin copolymer (A) stated above.

[0046] The density (ASTM D 1505) of the high pressure low density polyethylene (B) is usually 910 to 930 kg/m³, preferably 915 to 930 kg/m³, and more preferably 915 to 925 kg/m³.

[0047] The melt flow rate (MFR; ASTM D 1238, 190°C, 2.16 kg load) of the high pressure low density polyethylene (B) is within a range of 0.1 to 50 g/10 min, preferably 0.5 to 20 g/10 min, and more preferably 0.5 to 10 g/10 min. When the melt flow rate is within the above range, a composition with excellent moldability, which can provide a high strength crosslinked foam, can be obtained.

[0048] The high pressure low density polyethylene (B) is used, as necessary, in a proportion of 5 to 100 parts by weight, preferably 10 to 70 parts by weight, and more preferably 15 to 45 parts by weight based on 100 parts by weight of the ethylene/ α -olefin copolymer (A). When the high pressure low density polyethylene (B) is used in the above proportion, an elastomeric composition that can provide crosslinked foam having high strength and excellent tear strength can be obtained.

Ethylene/vinyl acetate copolymer (C)

[0049] The ethylene/vinyl acetate copolymer (C), that is optionally used in the present invention, is obtained by copolymerization of ethylene and vinyl acetate.

[0050] The ethylene/vinyl acetate copolymer (C) contains 10 to 30% by weight, preferably 15 to 30% by weight, and more preferably 15 to 25% by weight of vinyl acetate unit.

[0051] The melt flow rate (MFR; ASTM D 1238, 190°C, 2.16 kg load) of the ethylene/vinyl acetate copolymer (C) is within a range of 0.1 to 50 g/10 min, preferably 0.5 to 20 g/10 min, and more preferably 0.5 to 10 g/10 min.

[0052] The ethylene/vinyl acetate copolymer (C) is used, as necessary, in a proportion of more than 0 part by weight to 1,900 parts by weight, preferably 5 to 1,900 parts by weight, based on 100 parts by weight of the ethylene/ α -olefin copolymer (A). When the ethylene/vinyl acetate copolymer (C) is used in the above proportion, an elastomeric composition that can provide a crosslinked foam having excellent tear strength can be obtained.

Organic peroxide (D)

[0053] Examples of organic peroxides (D) used as a crosslinking agent in the present invention include dicumyl peroxide, di-*t*-butyl peroxide, 2,5-dimethyl-2,5-di-(*t*-butyl peroxy)hexane, 2,5-dimethyl-2,5-di-(*t*-butyl peroxy)hexyne-3, 1,3-bis(*t*-butyl peroxy isopropyl)benzene, 1,1-bis(*t*-butyl peroxy)-3,3,5-trimethylcyclohexane, *n*-butyl-4,4-bis(*t*-butyl peroxy)valerate, benzoyl peroxide, *p*-chlorobenzoyl peroxide, 2,4-dichlorobenzoyl peroxide, *t*-butyl peroxy benzoate, *t*-butyl perbenzoate, *t*-butyl peroxy isopropyl carbonate, diacetyl peroxide, lauroyl peroxide, *t*-butyl cumyl peroxide, etc.

[0054] In the present invention, the organic peroxide (D) is used in a proportion of usually 0.1 to 1.5 parts by weight, preferably 0.2 to 1.0 parts by weight, based on 100 parts by weight of the total amount of the ethylene/ α -olefin copolymer (A), the high pressure low density polyethylene (B) and the ethylene/vinyl acetate copolymer (C). When the organic peroxide (D) is used in the above proportion together with a crosslinking assistant (E), a crosslinked foam having an appropriate crosslinked structure can be obtained.

Crosslinking assistant (E)

[0055] Examples of crosslinking assistants (E) used in the present invention include peroxy crosslinking assistants such as sulfur, *p*-quinone dioxime, *p,p'*-dibenzoyl quinone dioxime, *N*-methyl-*N*-4-dinitrosoaniline, nitrosobenzene, diphenylguanidine and trimethylolpropane-*N,N'*-*m*-phenylenedimaleimide, divinylbenzene, triallyl cyanurate (TAC) and triallyl isocyanurate (TAIC). Moreover, the examples also include multifunctional methacrylate monomers such as ethylene glycol dimethacrylate, diethylene glycol dimethacrylate, polyethylene glycol dimethacrylate, trimethylolpropane trimethacrylate and allyl methacrylate, and multifunctional vinyl monomers such as vinyl butylate and vinyl stearate. Of these, triallyl cyanurate (TAC) and triallyl isocyanurate (TAIC) are preferable.

[0056] In the present invention, the crosslinking assistant (E) as stated above is desirably used in an amount where the weight ratio [(E)/(D)] of the crosslinking assistant (E) to the organic peroxide (D) is 1/30 to 5/1, preferably 1/20 to 3/1, and more preferably 1/15 to 2/1.

Foaming agent (F)

[0057] Examples of foaming agents (F) used in the present invention include organic pyrolytic foaming agents such as azodicarbonamide (ADCA), N,N'-dinitrosopentamethylenetetramine, 4,4'-oxybis(benzenesulfonyl hydrazide), diphenylsulfone-3,3'-disulfonyl hydrazide, p-toluenesulfonyl semicarbazide and trihydrazinotriazine, and inorganic pyrolytic foaming agents such as sodium hydrogen carbonate, sodium carbonate, ammonium hydrogen carbonate and ammonium carbonate. Of these, azodicarbonamide (ADCA) and sodium hydrogen carbonate are particularly preferable.

[0058] The foaming agent (F) is used in the present invention in a proportion of usually 3 to 20 parts by weight, preferably 5 to 15 parts by weight, based on 100 parts by weight of the total amount of the ethylene/ α -olefin copolymer (A), the high pressure low density polyethylene (B) and the ethylene/vinyl acetate copolymer (C). When the foaming agent (F) is used in the above proportion, a foamed product having a high expansion ratio and a closed cell ratio can be obtained. The amount of the foaming agent (F) is determined considering the expansion ratio of the crosslinked foam.



Organic metal compound (G)

[0059] The organic metal compound (G) used in the present invention has, per one molecule, at least two groups containing unsaturated carbon bond and at least one atom selected from oxygen, sulfur and nitrogen.

[0060] The organic metal compound (G) is a compound of metal selected from Groups 2 to 12 of the periodic table. Among them, metals of Groups 3 to 12 are classified into transition metal. That is, compounds of metals of Groups 3 to 12 are organic transition metal compounds. In the present invention, preferred metals are Groups 2 and 12, more preferred are Mg and Zn, and particularly preferred is Zn.

[0061] The group containing unsaturated carbon bond and at least one atom selected from oxygen, sulfur and nitrogen is preferably a group having a structure wherein oxygen atom, sulfur atom or nitrogen atom is directly bonded to the metal atom, more preferably unsaturated aliphatic carboxyl group, and particularly $\text{CH}_2=\text{CH}-\text{CO}-\text{O}-$ and $\text{CH}_2=\text{C}(\text{CH}_3)-\text{CO}-\text{O}-$.

[0062] The organic metal compound (G) used in the present invention has at least two $\text{CH}_2=\text{CH}-\text{CO}-\text{O}-$ or $\text{CH}_2=\text{C}(\text{CH}_3)-\text{CO}-\text{O}-$ groups per molecule, and a zinc compound is preferably used as an organic metal compound. Specifically, zinc diacrylate (ZDA) or zinc dimethacrylate (ZDMA) represented by the respective formulas shown below is preferable:



[0063] ZDA may simply be called "zinc acrylate". Similarly, ZDMA may simply be called "zinc methacrylate".

[0064] The organic metal compounds (G) include those formed in composition by a reaction during melt-extrusion of, for example, metal oxide such as zinc oxide and organic compound such as acrylic acid and methacrylic acid together with the aforementioned components (A) to (F).

[0065] The above organic metal compound (G) is used in a proportion of 0.05 to 5 parts by weight, preferably 0.05 to 4 parts by weight, more preferably 0.1 to 2 parts by weight, based on 100 parts by weight of the total amount of the ethylene/ α -olefin copolymer (A), the high pressure low density polyethylene (B) and the ethylene/vinyl acetate copolymer (C). When the organic metal compound (G) is used in the above proportion, foaming cells become more fine and homogeneous since the gel fraction in the obtained crosslinked foam increases. As a result, mechanical properties of the crosslinked foam such as compression set, tear strength and impact resilience are enhanced.

Olefinic elastomer crosslinked foam

[0066] The olefinic elastomer crosslinked foam of the present invention can be obtained by crosslinking and foaming the above-stated elastomeric composition for preparing an olefinic elastomer crosslinked foam of the present invention, which is usually performed under conditions of a temperature of 130°C to 200°C and a load of 30 to 300 kgf/cm² for 10 to 90 minutes. However, the time period of the crossing and foaming can be altered appropriately beyond the above-defined range, depending on the thickness of a mold.

[0067] Moreover, the olefinic elastomer crosslinked foam of the present invention may be a crosslinked foam obtained by compression molding of the formed article obtained by crosslinking and foaming under the above conditions, under the following conditions: a temperature of 130°C to 200°C, a loading of 30 to 300 kgf/cm², and a compression ratio of 1.1 to 3, preferably 1.3 to 2 for 5 to 60 minutes.

[0068] These crosslinked foams have a specific gravity (JIS K 7222) of 0.05 to 0.25, a surface hardness (Asker C hardness; JIS S 6050) of 20 to 80, and a gel fraction of 70% or more, usually 80 to 99%.

[0069] The olefinic elastomer crosslinked foam of the present invention having the above properties has a low compression set, high tear strength and high impact resilience.

[0070] The gel fraction (gel content = xylene-insoluble fraction) is determined as follows:

[0071] An olefinic elastomer crosslinked foam sample was weighed and cut into small pieces, and then the obtained pieces and xylene were placed into a closed container and refluxed for 3 hours.

[0072] Subsequently, the sample was placed on a filter for absolute drying. The weight of the dried residue minus the weight of xylene-insoluble components (e.g. a filler, a bulking agent, a pigment, etc.) other than polymeric components is defined as "corrected final weight (Y)".

[0073] The weight of the sample minus both the weight of xylene-soluble components (e.g. a stabilizer etc.) other than polymeric components and the weight of xylene-insoluble components (e.g. a filler, a bulking agent, a pigment, etc.) other than polymeric components is defined as "corrected initial weight (X)".

[0074] Now, gel content (xylene-insoluble fraction) is determined by the following formula:

$$\text{Gel fraction [\% by weight]} = [\text{corrected final weight (Y)}] \text{ divided by } [\text{corrected initial weight (X)}] \times 100$$

Preparation of olefinic elastomer crosslinked foam

[0075] The olefinic elastomer crosslinked foam of the present invention can be prepared, for an example, by the following method.

[0076] The above-stated various components of the elastomeric composition for preparing an olefinic elastomer crosslinked foam of the present invention are mixed with a Henschel mixer, and the obtained mixture is then subjected to melt mixing with a Banbury mixer, a roll or an extruder. In this melt mixing process, the mixture should be mixed and kneaded under the decomposition temperature of the foaming agent (F) and the organic peroxide (D) as a crosslinking agent. More specifically, the mixture should be mixed and kneaded under a condition where the temperature of the composition in a molten state is set at 100°C to 140°C, so that the composition becomes homogeneous.

[0077] In addition to the above-described ethylene/ α -olefin copolymer (A), high pressure low density polyethylene (B), ethylene/vinyl acetate copolymer (C), organic peroxide (D), crosslinking assistant (E), foaming agent (F) and/or organic metal compound (G), the composition of the present invention may optionally include fillers such as talc, calcium carbonate, aluminum hydroxide and magnesium hydroxide, or various additives such as a heat stabilizer, a weathering stabilizer, a flame retardant, an absorbent for hydrochloric acid, a pigment, a lubricant and a slip agent to the extent that they do not impair the object of the present invention.

[0078] A sheet of the elastomeric composition for preparing an olefinic elastomer crosslinked foam of the present invention can be obtained, for example, sheeting mixture obtained by the above mixing and kneading process by a calendaring machine, pressing machine or T-die extruder. In this sheet forming process, the mixture should be sheet formed under the decomposition temperature of foaming agent (F) and organic peroxide (D). More specifically, the mixture should be sheet formed under a condition where the temperature of the composition in a molten state is set at 100°C to 140°C.

[0079] The sheeted composition obtained by the above sheet forming process is cut to size within a ratio range of 1.0 to 1.2 time based on the capacity of a mold kept at a temperature of 130 °C to 200°C, and then the piece is inserted into the mold. The primary crosslinked foam is prepared by process comprising melting the composition under conditions of a clamping pressure of 30 to 300 kgf/cm² and a retention time of 10 to 90 minutes, performing crosslinking reaction and decomposition of foaming agent, and opening the mold to foam the composition.

[0080] The form of the above mold used for forming the crosslinked foaming is not particularly limited, but generally a mold having a form from which a sheet can be obtained is used. This mold used for forming the crosslinked foaming should have a fully closed structure so that molten resin and gases generated by decomposition of the foaming agent do not escape. Moreover, a retaining mold preferably has a taper inside for release of the resin from the mold.

[0081] The primary crosslinked foam obtained by the above method is then formed to a predetermined shape by compression molding. The conditions for this compression molding are: a mold temperature of 130°C to 200°C, a clamping pressure of 30 to 300 kgf/cm², a compression time of 5 to 60 minutes, and a compression ratio within a range of 1.1 to 3.0.

Footwear parts

[0082] The footwear parts of the present invention is made of the olefinic elastomer crosslinked foam of the present invention described above.

[0083] Examples of the footwear parts include sandals and the soles, midsoles, and innersoles of shoes.

EFFECT OF THE INVENTION

[0084] The present invention provides an elastomeric composition for preparing an olefinic elastomer crosslinked foam that can provide an olefinic elastomer crosslinked foam having an Asker C hardness of 20 to 80, a low specific gravity, a low compression set (CS), an excellent tear strength and impact resilience, and crosslinked foam made of this.

[0085] Moreover, the present invention provides footwear parts made of the above olefinic elastomer crosslinked foam, e.g. sandals, and soles, midsoles, and innersoles of shoes.

Examples

[0086] The present invention will be further described in the following examples. The examples are provided for illustrative purposes only, and are not intended to limit the scope of the invention.

[0087] For each of the crosslinked foams obtained in the Examples and Comparative examples, specific gravity, compression set, tear strength, Asker C hardness (surface hardness) and impact resilience were determined by the following method. Moreover, the gel fraction (gel content) was determined by the above-stated method.

(1) Specific gravity

[0088] Specific gravity was determined according to JIS K 7222.

(2) Compression set

[0089] A compression set test was carried out under conditions of 50°C × 6 hrs and a compression amount of 50% to determine compression set (CS), in accordance with JIS K 6301.

(3) Tear strength

[0090] A tear strength test was carried out at a pulling rate of 100 mm/min to determine tear strength, in accordance with BS5131-2.6.

(4) Asker C hardness

[0091] Asker C hardness was determined according to "Method for carrying out a spring hardness test (type C test)" described in attachment 2 of JIS K7312-1996.

(5) Impact resilience

[0092] Impact resilience was determined according to JIS K6255.

[0093] Ethylene/α-olefin copolymers used in the Examples and Comparative examples are as follows:

(1) Ethylene/1-butene copolymer (A1)

MFR (ASTM D 1238, 190°C, 2.16 kg load) = 0.5 g/10 min

Density (ASTM D 1505) = 885 kg/m³

Mw/Mn = 2.0

MFR₁₀/MFR_{2.16} = 6.0

(2) Ethylene/1-butene copolymer (A2)

MFR (ASTM D 1238, 190°C, 2.16 kg load) = 0.5 g/10 min

Density (ASTM D 1505) = 885 kg/m³

Mw/Mn = 2.1

MFR₁₀/MFR_{2.16} = 10.4

(3) Ethylene/1-butene copolymer (A3)

MFR (ASTM D 1238, 190°C, 2.16 kg load) = 3.6 g/10 min

Density (ASTM D 1505) = 895 kg/m³

Mw/Mn = 2.1

MFR₁₀/MFR_{2.16} = 5.7

(4) Ethylene/1-butene copolymer (A4)

EP 1 229 076 B1

MFR (ASTM D 1238, 190°C, 2.16 kg load) = 3.6 g/10 min

Density (ASTM D 1505) = 895 kg/m³

Mw/Mn = 2.0

MFR₁₀/MFR_{2.16} = 8.3

(5) Ethylene/1-butene copolymer (A5)

MFR (ASTM D 1238, 190°C, 2.16 kg load) = 1.2 g/10 min

Density (ASTM D 1505) = 905 kg/m³

Mw/Mn = 2.1

MFR₁₀/MFR_{2.16} = 5.9

(6) Ethylene/1-hexene copolymer (A6)

MFR (ASTM D 1238, 190°C, 2.16 kg load) = 1.3 g/10 min

Density (ASTM D 1505) = 905 kg/m³

Mw/Mn = 3.0

MFR₁₀/MFR_{2.16} = 6.5

[Example 1]

[0094] 25 parts by weight of the above ethylene/1-butene copolymer (A1), 45 parts by weight of the above ethylene/1-butene copolymer (A3), 30 parts by weight of the above ethylene/1-hexene copolymer (A6), 3 parts by weight of zinc oxide, 1 part by weight of stearic acid, 4 parts by weight of titanium white, 0.6 parts by weight of dicumyl peroxide, 0.15 parts by weight of triallyl cyanurate, 7.0 parts by weight of azodicarbonamide and 0.4 parts by weight of zinc acrylate were mixed and kneaded for 10 minutes with twin rolls having a roll surface temperature of 120°C, and the mixture was then molded into a sheet shape.

[0095] After being filled in a press mold, the obtained sheet was pressurized and heated under conditions of 150 kg/cm², 155°C and 30 minutes to obtain the primary crosslinked foam. The size of the press mold was 15 mm in thickness, 150 mm in length and 200 mm in width.

[0096] Then, the primary crosslinked foam was compression molded under conditions of 155°C, 150 kg/cm² and 10 minutes to obtain the secondary crosslinked foam. The size of the thus obtained secondary crosslinked foam was 15 mm in thickness, 160 mm in length and 250 mm in width.

[0097] Subsequently, the specific gravity, compression set, tear strength, Asker C hardness, impact resilience and gel fraction of the secondary crosslinked foam were determined according to the above-described methods. The results are shown in Table 1.

[Example 2]

[0098] Example 2 was carried out according to the same method as Example 1 with the exception that 25 parts by weight of ethylene/1-butene copolymer (A2) was used instead of 25 parts by weight of ethylene/1-butene copolymer (A1) and that 45 parts by weight of ethylene/1-butene copolymer (A4) was used instead of 45 parts by weight of ethylene/1-butene copolymer (A3). The results are shown in Table 1.

[Example 3]

[0099] 18.8 parts by weight of the above ethylene/1-butene copolymer (A1), 50 parts by weight of the above ethylene/1-butene copolymer (A3), 31.2 parts by weight of the above ethylene/1-hexene copolymers (A6), 25 parts by weight of the above high pressure low density polyethylene (HPLDPE; density (ASTM D 1505) = 920 kg/m³, MFR (ASTM D 1238, 190°C, 2.16 kg load) = 3.0 g/10 min), 3 parts by weight of zinc oxide, 1 part by weight of stearic acid, 4 parts by weight of titanium white, 0.6 parts by weight of dicumyl peroxide, 0.15 parts by weight of triallyl cyanurate, 7.0 parts by weight of azodicarbonamide and 0.4 parts by weight of zinc acrylate were mixed and kneaded for 10 minutes with twin rolls having a roll surface temperature of 120°C, and the mixture was then molded into a sheet shape.

[0100] The obtained sheet was filled in a press mold, and then was pressurized and heated under conditions of 150 kg/cm², 155°C and 30 minutes to obtain the primary crosslinked foam. The size of the press mold was 15 mm in thickness, 150 mm in length and 200 mm in width.

[0101] Then, the primary crosslinked foam was compression molded under conditions of 155°C, 150 kg/cm² and 10 minutes to obtain the secondary crosslinked foam. The size of the thus obtained secondary crosslinked foam was 15 mm in thickness, 160 mm in length and 250 mm in width.

[0102] Subsequently, the specific gravity, compression set, tear strength, Asker C hardness, impact resilience and gel fraction of the secondary crosslinked foam were determined according to the above-described methods. The results are shown in Table 1.

EP 1 229 076 B1

[Comparative example 1]

[0103] Comparative example 1 was carried out in the same manner as Example 1 with the only exception that zinc acrylate was not used therein. The results are shown in Table 1.

5

10

15

20

25

30

35

40

45

50

55

Table 1

Composition of elastomeric composition [part by weight]		Example 1	Example 2	Example 3	Comparative example 1
Copolymer (A1)	25	-	18.8	25	-
Copolymer (A2)	-	25	-	-	-
Copolymer (A3)	45	-	50	45	-
Copolymer (A4)	-	45	-	-	-
Copolymer (A6)	30	30	31.2	30	-
HPLDPE	-	-	25	-	-
Zinc oxide	3	3	3	3	3
Stearic acid	1	1	1	1	1
Titanium white	4	4	4	4	4
Dicumyl peroxide	0.6	0.6	0.6	0.6	0.6
Triallyl cyanurate	0.15	0.15	0.15	0.15	0.15
Azodicarbonamide	7.0	7.0	7.0	7.0	7.0
Zinc acrylate	0.4	0.4	0.4	0.4	-
Properties of the secondary crosslinked foam					
Specific gravity [g/cm ³]	0.13	0.13	0.14	0.13	0.13
Gel fraction [%]	86	84	84	84	78
Asker C hardness	55	57	61	55	55
Tear strength [kg/cm]	3.1	3.0	3.3	2.7	2.7
Compression set [%]	38	40	37	43	43
Impact resilience [%]	65	65	62	62	62

[Example 4]

[0104] 33.3 parts by weight of the above ethylene/1-butene copolymer (A3), 66.7 parts by weight of the above ethylene/1-hexene copolymer (A6), 122 parts by weight of ethylene/vinyl acetate copolymer [EVA; vinyl acetate content = 21% by weight, MFR (ASTM D 1238, 190°C, 2.16 kg load) = 1.5 g/10 min], 3 parts by weight of zinc oxide, 1 part by weight of stearic acid, 4 parts by weight of titanium white, 0.6 parts by weight of dicumyl peroxide, 0.15 parts by weight of triallyl cyanurate, 6.5 parts by weight of azodicarbonamide and 0.4 parts by weight of zinc acrylate were mixed and kneaded for 10 minutes with twin rolls having a roll surface temperature of 120°C, and the mixture was then molded into a sheet shape.

[0105] The obtained sheet was filled in a press mold, and then was pressurized and heated under conditions of 150 kg/cm², 155°C and 30 minutes to obtain the primary crosslinked foam. The size of the press mold was 15 mm in thickness, 150 mm in length and 200 mm in width.

[0106] Then, the primary crosslinked foam was compression molded under conditions of 155°C, 150 kg/cm² and 10 minutes to obtain the secondary crosslinked foam. The size of the thus obtained secondary crosslinked foam was 15 mm in thickness, 160 mm in length and 250 mm in width.

[0107] Subsequently, the specific gravity, compression set, tear strength, Asker C hardness, impact resilience and gel fraction of the secondary crosslinked foam were determined according to the above-described methods. The results are shown in Table 2.

[Example 5]

[0108] Example 5 was carried out in the same manner as Example 4 with the only exception that 66.7 parts by weight of ethylene/1-butene copolymer (A5) was used instead of 66.7 parts by weight of ethylene/1-hexene copolymer (A6). The results are shown in Table 2.

[Comparative example 2]

[0109] Comparative example 2 was carried out in the same manner as Example 4 with the only exception that zinc acrylate was not used therein. The results are shown in Table 2.

[Comparative example 3]

[0110] Comparative example 3 was carried out in the same manner as Example 5 with the only exception that zinc acrylate was not used therein. The results are shown in Table 2.

Table 2

	Example 4	Example 5	Comparative example 2	Comparative example 3
Composition of elastomeric composition [part by weight]				
Copolymer (A3)	33.3	33.3	33.3	33.3
Copolymer (A5)	-	66.7	-	66.7
Copolymer (A6)	66.7	-	66.7	-
EVA	122	122	122	122
Zinc oxide	3	3	3	3
Stearic acid	1	1	1	1
Titanium white	4	4	4	4
Dicumyl peroxide	0.6	0.6	0.6	0.6
Triallyl cyanurate	0.15	0.15	0.15	0.15
Azodicarbonamide	6.5	6.5	6.5	6.5
Zinc acrylate	0.4	0.4	-	-
Properties of the secondary crosslinked foam				
Specific gravity [g/cm ³]	0.14	0.14	0.14	0.14
Gel fraction [%]	85	86	79	80
Asker C hardness	54	55	55	55
Tear strength [kg/cm]	3.0	3.0	2.6	2.6
Compression set [%]	43	43	47	47
Impact resilience [%]	62	61	56	57

Claims

1. An elastomeric composition for preparing an olefinic elastomer crosslinked foam, comprising:

an ethylene/ α -olefin copolymer (A) which contains 85 to 99 mole% of units derived from ethylene and which has a density (ASTM D 1505) of 880 to 920 kg/m³, and a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) MFR_{2.16} of 0.1 to 10 g/10 min;
 optionally, a high pressure low density polyethylene (B) which contains less than 1 mole% of units derived from an α -olefin having 3 to 10 carbon atoms and which has a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) of 0.1 to 50 g/10 min;
 optionally, an ethylene/vinyl acetate copolymer (C) which has a vinyl acetate content of 10 to 30% by weight and a melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) of 0.1 to 50 g/10 min;
 an organic peroxide (D);
 a crosslinking assistant (E);
 a foaming agent (F); and
 0.05 to 5 parts by weight, based on 100 parts by weight of the total amount of the ethylene/ α -olefin copolymer (A), the high pressure low density polyethylene (B) and the ethylene/vinyl acetate copolymer (C), of an organic metal compound (G) which is a compound of metal selected from Groups 2 to 12 of the periodic table and which has at least two groups containing unsaturated carbon bond and at least one atom selected from oxygen, sulfur and nitrogen per molecule.

2. The elastomeric composition according to claim 1 comprising, based on 100 parts by weight of said ethylene/ α -olefin copolymer (A), 5 to 100 parts by weight of said high pressure low density polyethylene (B).

3. The elastomeric composition according to claim 1 or 2 comprising, based on 100 parts by weight of said ethylene/ α -olefin copolymer (A), 5 to 1,900 parts by weight of said ethylene/vinyl acetate copolymer (C).

4. The elastomeric composition according to any one of claims 1 to 3, wherein the α -olefin in said ethylene/ α -olefin copolymer (A) is an α -olefin having 3 to 10 carbon atoms.

5. The elastomeric composition according to any one of claims 1 to 4, wherein there is used, as said ethylene/ α -olefin copolymer (A), a mixture of two or more ethylene/ α -olefin copolymers, having a molecular weight distribution (Mw/Mn) determined by gel permeation chromatography (GPC) within the range of 1.5 to 4 and a ratio (MFR₁₀/MFR_{2.16}) of the melt flow rate (ASTM D 1238, 190°C, 2.16 kg load) MFR_{2.16} to the melt flow rate (ASTM D 1238, 190°C, 10 kg load) MFR₁₀ within the range of 5 to 20.

6. The elastomeric composition according to claim 5, wherein said mixture of two or more of the ethylene/ α -olefin copolymers is produced by blending or multistage polymerization so that it has a molecular weight distribution (Mw/Mn) determined by GPC within the range of 2.3 to 6.

7. The elastomeric composition according to claim 1, wherein said organic metal compound (G) has at least two $\text{CH}_2=\text{CH}-\text{CO}-\text{O}-$ or $\text{CH}_2=\text{C}(\text{CH}_3)-\text{CO}-\text{O}-$ groups per molecule.

8. The elastomeric composition according to claim 7, wherein said organic metal compound (G) is an organic zinc compound.

9. The elastomeric composition according to claim 8, wherein said organic zinc compound is zinc diacrylate or zinc dimethacrylate.

10. An olefinic elastomer crosslinked foam, which is obtained by crosslinking and foaming the elastomeric composition for preparing olefinic elastomer crosslinked foam according to any one of claims 1 to 9.

11. An olefinic elastomer crosslinked foam, which is obtained by a secondary compression of the crosslinked foam according to claim 10.

12. The olefinic elastomer crosslinked foam according to claim 11, wherein said secondary compression is performed under conditions of a temperature of 130°C to 200°C and a load of 2.9 to 29 MPa (30 to 300 kgf/cm²) for 5 to 60 minutes.

13. The olefinic elastomer crosslinked foam according to any one of claims 10 to 12 having a specific gravity (JIS K 7222) of 0.05 to 0.25, a surface hardness (Asker C hardness) of 20 to 80, and a gel fraction of 70% or more.

14. A footwear part, which is made of the crosslinked foam according to any one of claims 10 to 13.

15. The footwear part according to claim 14, which is a midsole, innersole or sole.

Patentansprüche

1. Elastomere Zusammensetzung zur Herstellung eines olefinischen vernetzten Elastomerschaums, umfassend:

ein Ethylen/ α -Olefin-Copolymer (A), das 85 bis 99 mol-% von aus Ethylen stammenden Einheiten enthält und eine Dichte (ASTM D 1505) von 880 bis 920 kg/m³ und eine Schmelzflussrate (ASTM D 1238, 190°C, 2,16 kg Last) MFR_{2,16} von 0,1 bis 10 g/10 min hat;

gegebenenfalls ein niederdichtetes Hochdruck-Polyethylen (B), das weniger als 1 mol-% von aus einem α -Olefin mit 3 bis 10 Kohlenstoffatomen stammenden Einheiten enthält und eine Schmelzflussrate (ASTM D 1238, 190°C, 2,16 kg Last) von 0,1 bis 50 g/10 min hat;

gegebenenfalls ein Ethylen/Vinylacetat-Copolymer (C), das einen Vinylacetatgehalt von 10 bis 30 Gew.% und eine Schmelzflussrate (ASTM D 1238, 190°C, 2,16 kg Last) von 0,1 bis 50 g/10 min hat;

ein organisches Peroxid (D);

eine Vernetzungshilfe (E);

einen Schaumbildner (F); und

0,05 bis 5 Gew.-Teile, bezogen auf 100 Gew.-Teile der Gesamtmenge aus dem Ethylen/ α -Olefin-Copolymer (A), dem niederdichten Hochdruck-Polyethylen (B) und dem Ethylen/Vinylacetat-Copolymer (C), einer organischen Metallverbindung (G), die eine Verbindung eines Metalls ist, das aus den Gruppen 2 bis 12 des Periodensystems ausgewählt ist, und die wenigstens zwei Gruppen, die eine ungesättigte Kohlenstoffbindung enthalten, und wenigstens ein Atom, das aus Sauerstoff, Schwefel und Stickstoff ausgewählt ist, pro Molekül aufweist.

2. Elastomere Zusammensetzung gemäss Anspruch 1, die, bezogen auf 100 Gew.-Teile des Ethylen/ α -Olefin-Copolymers (A), 5 bis 100 Gew.-Teile des niederdichten Hochdruck-Polyethylens (B) umfasst.

3. Elastomere Zusammensetzung gemäss Anspruch 1 oder 2, die, bezogen auf 100 Gew.-Teile des Ethylen/ α -Olefin-Copolymers (A), 5 bis 1.900 Gew.-Teile des Ethylen/Vinylacetat-Copolymers (C) umfasst.

4. Elastomere Zusammensetzung gemäss einem der Ansprüche 1 bis 3, worin das α -Olefin im Ethylen/ α -Olefin-Copolymer (A) ein α -Olefin mit 3 bis 10 Kohlenstoffatomen ist.

5. Elastomere Zusammensetzung gemäss einem der Ansprüche 1 bis 4, worin als Ethylen/ α -Olefin-Copolymer (A) eine Mischung aus zwei oder mehr Ethylen/ α -Olefin-Copolymeren mit einer Molekulargewichtsverteilung (Mw/Mn), bestimmt durch Gelpermeationschromatographie (GPC), innerhalb des Bereichs von 1,5 bis 4 und einem Verhältnis (MFR₁₀/MFR_{2,16}) der Schmelzflussrate (ASTM D 1238, 190°C, 2,16 kg Last) MFR_{2,16} zur Schmelzflussrate (ASTM D 1238, 190°C, 10 kg Last) MFR₁₀ innerhalb des Bereichs von 5 bis 20 verwendet wird.

6. Elastomere Zusammensetzung gemäss Anspruch 5, worin die Mischung aus zwei oder mehreren der Ethylen/ α -Olefin-Copolymere durch Vermischen oder Mehrstufenpolymerisation erzeugt wird, so dass sie eine Molekulargewichtsverteilung (Mw/Mn), bestimmt durch GPC, innerhalb des Bereichs von 2,3 bis 6 hat.

7. Elastomere Zusammensetzung gemäss Anspruch 1, worin die organische Metallverbindung (G) wenigstens zwei CH₂=CH-CO-O- oder CH₂=C(CH₃)-CO-O-Gruppen pro Molekül aufweist.

8. Elastomere Zusammensetzung gemäss Anspruch 7, worin die organische Metallverbindung (G) eine organische Zinkverbindung ist.
9. Elastomere Zusammensetzung gemäss Anspruch 8, worin die organische Zinkverbindung Zinkdiacrylat oder Zinkdimethacrylat ist.
10. Olefinischer vernetzter Elastomerschaum, der durch Vernetzen und Schäumen der elastomeren Zusammensetzung zur Herstellung eines olefinischen vernetzten Elastomerschaums gemäss einem der Ansprüche 1 bis 9 erhalten wird.
11. Olefinischer vernetzter Elastomerschaum, der durch eine sekundäre Verpressung des vernetzten Schaums gemäss Anspruch 10 erhalten wird.
12. Olefinischer vernetzter Elastomerschaum gemäss Anspruch 11, worin die sekundäre Verpressung unter Bedingungen einer Temperatur von 130 bis 200°C und einer Last von 2,9 bis 29 MPa (30 bis 300 kgf/cm²) für 5 bis 60 Minuten durchgeführt wird.
13. Olefinischer vernetzter Elastomerschaum gemäss einem der Ansprüche 10 bis 12 mit einer spezifischen Dichte (JIS K 7222) von 0,05 bis 0,25, einer Oberflächenhärte (Asker-C-Härte) von 20 bis 80 und einer Gelfraktion von 70 % oder mehr.
14. Schuhwerkteil, das aus dem vernetzten Schaum gemäss einem der Ansprüche 10 bis 13 hergestellt ist.
15. Schuhwerkteil gemäss Anspruch 14, das eine Zwischensohle, Innensohle oder Sohle ist.

Revendications

1. Composition élastomère pour préparer une mousse réticulée d'élastomère oléfinique, comprenant :

un copolymère d'éthylène/ α -oléfine (A) qui contient de 85 à 99 % en mole de motifs dérivés de l'éthylène et qui a une densité (ASTM D 1505) de 880 à 920 kg/m³ et une vitesse d'écoulement en masse fondue (ASTM D 1238, 190 °C, 2,16 kg de charge) MFR_{2,16} de 0,1 à 10 g/10 minutes ;
optionnellement, un polyéthylène à faible densité à haute pression (B) qui contient moins de 1 % en mole de motifs dérivés d'une α -oléfine ayant de 3 à 10 atomes de carbone et qui a une vitesse d'écoulement en masse fondue (ASTM D 1238, 190 °C, 2,16 kg de charge) de 0,1 à 50 g/10 minutes ;
optionnellement, un copolymère d'éthylène/acétate de vinyle (C) qui a une teneur en acétate de vinyle de 10 à 30 % en poids et une vitesse d'écoulement en masse fondue (ASTM D 1238, 190 °C, 2,16 kg de charge) de 0,1 à 50 g/10 minutes ;
un peroxyde organique (D) ;
un assistant de réticulation (E) ;
un agent moussant (F) ; et
0,05 à 5 parties en poids, sur la base de 100 parties en poids de la quantité totale du copolymère d'éthylène/ α -oléfine (A), du polyéthylène à faible densité à haute pression (B) et du copolymère d'éthylène/acétate de vinyle (C), d'un composé de métal organique (G) qui est un composé de métal choisi dans les Groupes 2 à 12 du tableau périodique et qui a au moins deux groupes contenant une liaison de carbone insaturée et au moins un atome choisi parmi l'oxygène, le soufre et l'azote par molécule.

2. Composition élastomère selon la revendication 1 comprenant, sur la base de 100 parties en poids dudit copolymère d'éthylène/ α -oléfine (A), 5 à 100 parties en poids dudit polyéthylène à faible densité à haute pression (B).
3. Composition élastomère selon la revendication 1 ou 2 comprenant, sur la base de 100 parties en poids dudit copolymère d'éthylène/ α -oléfine (A), 5 à 1900 parties en poids dudit copolymère d'éthylène/acétate de vinyle (C).
4. Composition élastomère selon l'une quelconque des revendications 1 à 3, dans laquelle l' α -oléfine dans ledit copolymère d'éthylène/ α -oléfine (A) est une α -oléfine ayant 3 à 10 atomes de carbone.
5. Composition élastomère selon l'une quelconque des revendications 1 à 4, dans laquelle il est utilisé, en tant que

ledit copolymère d'éthylène/ α -oléfine (A), un mélange de deux ou plus copolymères d'éthylène/ α -oléfine, ayant une distribution de poids moléculaire (M_w/M_n) déterminé par chromatographie par perméation de gel (GPC) dans la gamme de 1,5 à 4 et un rapport ($MFR_{10}/MFR_{2,16}$) de la vitesse d'écoulement en masse fondue (ASTM D 1238, 190 °C, 2,16 kg de charge) $MFR_{2,16}$ sur la vitesse d'écoulement en masse fondue (ASTM D 1238, 190 °C, 10 kg de charge) MFR_{10} dans la gamme de 5 à 20.

6. Composition élastomère selon la revendication 5, dans laquelle ledit mélange de deux ou plus copolymères d'éthylène/ α -oléfine est produit par polymérisation à étages multiples ou par mélange de manière à ce qu'il ait une distribution de poids moléculaire (M_w/M_n) déterminé par GPC dans la gamme de 2,3 à 6.
7. Composition élastomère selon la revendication 1, dans laquelle ledit composé de métal organique (G) a au moins deux groupes $CH_2=CH-CO-O-$ ou $CH_2=C(CH_3)-CO-O-$ par molécule.
8. Composition élastomère selon la revendication 7, dans laquelle ledit composé de métal organique (G) est un composé de zinc organique.
9. Composition élastomère selon la revendication 8, dans laquelle ledit composé de zinc organique est un diacrylate de zinc ou un diméthacrylate de zinc.
10. Mousse réticulée d'élastomère oléfinique, qui est obtenue en réticulant et en faisant mousser la composition élastomère afin de préparer une mousse réticulée d'élastomère oléfinique selon l'une quelconque des revendications 1 à 9.
11. Mousse réticulée d'élastomère oléfinique, qui est obtenue par une compression secondaire de la mousse réticulée selon la revendication 10.
12. Mousse réticulée d'élastomère oléfinique selon la revendication 11, dans laquelle ladite compression secondaire est effectuée sous des conditions d'une température de 130 °C à 200 °C et une charge de 2,9 à 29 MPa (30 à 300 kgf/cm²) pendant 5 à 60 minutes.
13. Mousse réticulée d'élastomère oléfinique selon l'une quelconque des revendications 10 à 12 ayant une densité (JIS K 7222) de 0,05 à 0,25, une dureté de surface (dureté Asker C) de 20 à 80 et une fraction de gel de 70 % ou plus.
14. Partie de chaussure, qui est faite de la mousse réticulée selon l'une quelconque des revendications 10 à 13.
15. Partie de chaussure selon la revendication 14, qui est un intercalaire, une semelle première ou une semelle.